

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (currently amended)        A method for treating a cellulosic grey fabric, comprising the following steps:

(a) a pretreatment step in which, in the presence of water, at a temperature of 80-100°C, the fabric is contacted with a thermostable enzyme which degrades starch; and

(b) an integrated desizing and scouring step in which, in the presence of water, at a temperature of 70°C at the most, the fabric as obtained in step (a) is contacted with an enzyme which degrades a polymeric component of the primary cell wall of cotton and an enzyme which degrades starch

wherein steps (a) and (b) are carried out as a continuous process and the fabric is subjected to each step for 5 minutes at the most.

2. (original)    A method according to claim 1, wherein, between steps (a) and (b), the fabric is subjected to a treatment in which the mass transport of fabric components to be washed away is promoted.

3. (original)    A method according to claim 2, wherein the treatment is a vacuum treatment or a blowing treatment.

4. (previously presented)        A method according to claim 1, wherein, in steps (a) and (b), the enzyme which degrades starch is an amylase.

5. (original) A method according to claim 4, wherein, in steps (a) and (b), the enzyme which degrades starch is an  $\alpha$ -amylase.

6. (previously presented) A method according to claim 1, wherein, in step (b), the enzyme which degrades a polymeric component of the primary cell wall of cotton is selected from the group of cellulase, protease and pectinase.

7. (original) A method according to claim 6, wherein, in step (b), the enzyme which degrades a polymeric component of the primary cell wall of cotton is a pectinase.

8. (original) A method according to claim 7, wherein the pectinase is a polygalacturonate lyase.

9. (previously presented) A method according to claim 1, wherein steps (a) and (b) are carried out in the presence of a surfactant.

10. (canceled).

11. (previously presented) A method according to claim 1, wherein step (a) is carried out at a temperature of 90-100°C.

12. (previously presented) A method according to claim 1, wherein step (b) is carried out at a temperature of 30-60°C.

13. (previously presented) A method according to claim 1, wherein steps (a) and (b) are carried out at a pH of 7.5-9.5.

14. (canceled).

15. (previously presented) A method according to claim 1, wherein the fabric obtained in step (b) is subjected to a washing treatment which is carried out at a temperature of 60-100°C in the presence of a surfactant.

16. (original) A method according to claim 15, wherein, between step (b) and the subsequent washing treatment, the fabric is subjected to a treatment in which the mass transport of fabric components to be washed away is promoted.

17. (original) A method according to claim 16, wherein the washed fabric is subsequently bleached.

18. (previously presented) A method according to claim 1, wherein the fabric is a woven cotton fabric.

19. (previously presented) A fabric manufactured according to the method of claim 1.

20. (canceled).

21. (previously presented) A textile product manufactured from a fabric treated using the method according to claim 1.